



US-HC-456

Heat Cure 1 Part Silicone Gel – 10 Shore A Hardness

1-part, heat cure silicone developed for conformal coating applications. It offers unprimed adhesion to metals and many plastics. Heated cures result in a tough and durable silicone conformal coating.

Product Features

- Neutral Addition Cure
- Fast heat cure
- Self-leveling liquid
- Fluoresces under UV light to enable coating inspection
- Adhesion to metals and many plastics
- Convenient 1 part system

Product Applications

- Coating electronic assemblies
- Industrial coating and sealing
- Thin section potting & encapsulation

Chemical cure system: Platinum catalyzed, addition cure system.

Typical Properties

Uncured

Specific Gravity: 0.98	Color: Clear	Solids: 100 %
Shelf Life: 12 MONTHS	Viscosity: 600 cps.	Tack Free Time at 110°C: 15 minutes

Cured 20 minutes at 110°C

Durometer, Shore A: 10	Dielectric Strength, kv/mm: 13
Dielectric Constant: 2.4	Dissipation Factor at 1kHz: 0.01
Thermal conductivity: 0.0005	

Application Methods: Apply by: pouring, dipping, brushing, flow-coat, spin-on or spraying.

Curing: Can be accomplished with heat to very rapid cures. Typical utilization involves dispensing in open air and oven, IR, or hot air curing.

Handling precautions: Avoid contact with tin cured RTV's, sulphur compounds, azides, imides, latex rubber gloves, and amines as cure system can be deactivated

Solids: 100% solids, contains no solvents

Adhesion: This product offers primerless adhesion to plastics, metals and typical substrates.

Service temperature: -65°C to +250°C continuous

Limitations: Do not use product in solvent or fuel immersion applications. Allow to fully cure before putting assembly into service.

Packaging: Available in 8 pound gallon cans, 40 lb. pails and 400 lb. drums. This product is also available in customer defined packaging upon request.

Handling and safety: For maximum shelf life, keep containers sealed when not in use. Keep out of the reach of children. Uncured sealant irritates eyes and skin. Refer to MSDS.

Shelf-life: Sealed containers guaranteed for 6 months from the ship date when stored in a cool dry area below 70°F.

Applicable standards: Conforms to GM low volatility requirements.